

We deliver superior performance and cost savings through sustainability and the transformation of recycled plastics into value-creating waxes and polymers.

TYPICAL PHYSICAL PROPERTIES

CERANOVUS POLYETHYLENE WAXES

	DENSITY (g/cm ³) ASTM D1298	DROP POINT (°C) ASTM D3954	NEEDLE PENETRATION @ 25°C in dmm (0.1 MM) ASTM D1321	VISCOSITY cps @ 140°C BROOKFIELD
A115	0.92	116	2	225
A120	0.93	122	2	700
A125	0.94	126	1	2025

CERANOVUS POLYPROPYLENE WAXES

	DENSITY (g/cm ³) ASTM D1298	DROP POINT (°C) ASTM D3954	NEEDLE PENETRATION @ 25°C in dmm (0.1 MM) ASTM D1321	VISCOSITY cps @ 190°C BROOKFIELD
A155	0.90	155	2	75



IMPROVE
PERFORMANCE



REDUCE
COSTS



ENHANCE
SUSTAINABILITY



GREENMANTRA[®]

TECHNOLOGIES

GreenMantra Technologies remains committed to producing and delivering products that exceed our customers expectations.



MADE WITH 100% RECYCLED CONTENT
PRE-CONSUMER AND POST-CONSUMER

Our products are available in pastilles. Packaging is available in Kraft bags and supersacks.

Please contact us for information on pricing, specifications and samples at info@greenmantra.com.